



6x36 WS = 6x[1+7+(7+7)+14] IWRC

Features:

- Galvanised rope lubricated with light dry lubrication A1 or dry
- Ungalvanised rope lubricated with heavy lubrication A1 or A2
- Also used for the manufacture of slings
- All rope manufactured generally to EN 12385
- Supplied with manufacturer's certificate of conformance
- Ideal for hot metal cranes, winches, drill rigs
- Available in left or right hand lay

Rope Diameter (mm)	Unit Weight kg/m	Wire Tensile	
		1770 N/mm ²	1960 N/mm ²
		Minimum Breaking Load (MBL) kN	
8.00	0.262	40.3	44.7
9.00	0.331	51.0	56.5
10.00	0.409	63.0	69.8
11.00	0.495	76.2	84.4
12.00	0.589	90.7	100.5
13.00	0.691	106.5	117.9
14.00	0.802	124	137
16.00	1.047	161	179
18.00	1.325	204	226
19.00	1.476	227	252
20.00	1.636	252	279
22.00	1.980	305	338
24.00	2.356	363	402
26.00	2.765	426	472
28.00	3.207	494	547
32.00	4.188	645	715
36.00	5.301	817	904
38.00	5.906	910	1008
40.00	6.544	1008	1116
42.00	7.215	1112	1231
44.00	7.918	1220	1351
48.00	9.423	1452	1608
50.00	10.225	1575	1744
52.00	11.059	1704	1887
56.00	12.826	1976	
62.00	15.540	2427	
64.00	17.710	2766	